

Address: No. 14, Beisanhuandonglu, Chaoyang district, Beijing, ChinaPost Code: 100013Tel: +86(0)1064208747, +86(0)1064200694, +86(0)1064216131-2479, 2484, 2436, 2465Fax: +86(0)1064208747, +86(0)1084290301Web site: www.plastic-test.net

No.2005 (X)0058

CUSTOMER:

Fangxing Building Materials Co., Ltd.

Fangxing Building Materials Co., Ltd.

Reinforced PVC corrugated sheet coated with Geloy

SAMPLES FOR TESTING

Name:

Manufacturer:

Appearance:

DATE OF RECEIPT: 2005-01-26

TEST PERIOD:

2005-01-26 to 2005-01-31


Red corrugated sheet

THIS REPORT COMPRISES 2 PAGES.

DIRECTOR:

露着

Address: No. 14, beisanhuandonglu, Chaoyang district, Beijing, China Post Code: 100013 Tel: +86(0)1064208747, +86(0)1064200694,+86(0)1064216131-2479, 2484, 2436, 2465 Fax:+86(0)1064208747, +86(0)1064216131-2485 E-mail: <u>plastic-test@brici.ac.cn</u> Web site: <u>www.plastic-test.net</u>



Address: No. 14, Beisanhuandonglu, Chaoyang district, Beijing, China Post Code: 100013 Tel: +86(0)1064208747, +86(0)1064200694, +86(0)1064216131-2479, 2484, 2436, 2465 Fax: +86(0)1064208747, +86(0)1084290301 Web site: www.plastic-test.net

TESTING RESULTS

No. 2005 (X)0058

No.	Item	Requirement	Results
1	Oxygen index	≥32	44
2	Horizontal burning	FH1	FH1
3	Vertical burning	FV0	FV0

CONCLUSIONS

The samples of the product referred to in this report have been tested in accordance with the specification GB 50222-1995 "Code for Fire Prevention in Design of Interior Decoration of Buildings". The fire prevention is classified as class B1 according to the standard and it can be used in common building and house.

(HEREINAFTER IS EMPTY

Test:利泉胡孝义



Page 2 of 2